

Highly impermeable reprofiling mortar

- waterproof
- excellent workability
- easy to level and finish
- very low rebound
- fulfils the German potable water requirements according to DVGW W300-5 (P):10-2014, type 1

| | | |
|--|--|--|
| Compressive strength | class R4 \geq 45 MPa | CE 0761 |
| Chloride ion content | \leq 0.05 % | |
| Adhesive bond | \geq 2.0 MPa | Vandex Isoliermittel-GmbH Industriestr. 21 DE-21493 Schwarzenbek 11/13 325 EN 1504-3:2005/ZA.1a VANDEX CEMLINE MG 4 FF CC repair mortar for structural repair (based on hydraulic cement) |
| Carbonation resistance | passed | |
| Modulus of elasticity | \geq 20 GPa | |
| Thermal compatibility | | |
| Part 1: Freeze thaw with de-icing salt immersion | \geq 2.0 MPa | |
| Capillary absorption | \leq 0.5 kg/m ² ·h ^{0.5} | |
| Reaction to fire | class A1 | |
| Dangerous substances | complies with 5.4 | |

PRODUCT DESCRIPTION

VANDEX CEMLINE MG 4 FF is a waterproof cementitious, ready-to-use reprofiling mortar.

AREAS OF APPLICATION

- substrates: concrete
- reprofiling and coating of soffits, walls and slabs
- suitable as smooth finish for drinking water tanks and industrial water installations

PROPERTIES

VANDEX CEMLINE MG 4 FF is applied in layers of 10 to 15 mm thickness in one working cycle. It is waterproof when applied in min. 8 mm layer thickness. The material has a very dense structure, thus a very low porosity and can easily be flattened.

VANDEX CEMLINE MG 4 FF is approved for application in contact with potable water and fulfils the corresponding German requirements according to DVGW W300-5 (P):10-2014, type 1.

SURFACE PREPARATION

The substrate to be treated must be sound and even, open-pored, roughened and its surface free from voids, large cracks or ridges. Any adhesion reducing substances like bitumen, oil, grease, remains of paint or laitance must be removed by suitable means.

Thoroughly moisten the substrate, it must be damp but not wet at the time of application. Any surface water on horizontal surfaces must be removed.

MIXING

Mix 25 kg of VANDEX CEMLINE MG 4 FF with 3.5-4.5 litres of tap water in a clean container for at least 3 minutes to a lump-free, homogeneous consistency. Use a mechanical mixer.

APPLICATION

VANDEX CEMLINE MG 4 FF is usually applied by a fine mortar spraying device, but it can also be applied by trowel. Apply a minimum of 8 mm (approx. 16 kg/m²) and a maximum of 15 mm (approx. 30 kg/m²) in one working cycle. For small areas such as coves or local repairs, VANDEX CEMLINE MG 4 FF may be applied in layer thicknesses up to 30 mm. If several coats are required it is recommended to apply the next coat whilst the previous coat is still damp at the surface.

Trowel application

First a scratch coat is applied for maximum adhesion to the substrate. Ensure that all cavities in the substrate are filled in order to exclude any trapped air.

On horizontal and slightly inclined surfaces it is possible to apply a bonding bridge with VANDEX BB 75. Apply by brush a small quantity of material into the surface until it is completely moist. The following VANDEX CEMLINE MG 4 FF layer must be applied wet in wet.

Spray application

VANDEX CEMLINE MG 4 FF can be applied with a suitable fine mortar spraying device. For maximum spray pattern it should be possible to adjust volume of product as well as air pressure and volume. The nozzle diameter is approx. 10 mm.

The material is applied in a circular motion with the spray nozzle held at a 90° angle to the substrate. The material is then flattened.

Do not apply at temperatures below +5 °C or to a frozen substrate.

CONSUMPTION

Approx. 2 kg/m² of VANDEX CEMLINE MG 4 FF is required to produce a layer thickness of 1 mm.

CURING

Provide a relative humidity of >85% in enclosed areas. Avoid formation of condensate and water film during the first 7 days after application.

While setting, surfaces exposed to weather must be kept moist for at least 5 days and be protected from extreme weather conditions (e.g. sun, wind, frost). The freshly treated surfaces should be protected from rain for a minimum period of 24 h.

FILLING OF WATER RETAINING STRUCTURES

Filling can take place when the surface treatment has hardened sufficiently, usually not less than 14 days after application. However, if earlier filling is specifically required, filling may be considered after not less than 7 days, provided the surface is thoroughly checked for hardness. A careful cleaning and disinfection prior to the first operation is essential.

Observe national laws and regulations.

PACKAGING

25 kg PE-lined paper bag

STORAGE

When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.

HEALTH AND SAFETY

Please refer to Safety Data Sheet on www.vandex.com.

| TECHNICAL DATA | | CEMLINE MG 4 FF (R4) |
|--|--------|----------------------|
| Appearance | | grey powder |
| Grain size d_{max} | [mm] | 2 |
| Density of fresh mortar | [kg/l] | approx. 2.2 |
| Application time, 20 °C | [min.] | approx. 45 |
| Curing time, 20 °C | [h] | approx. 2-6 |
| Compressive strength 28 d | [MPa] | approx. 55 |
| Bending tensile strength 28 d | [MPa] | approx. 7 |
| Static modulus of elasticity 28 d | [GPa] | approx. 35 |
| Waterproof 28 d, 1.5 bar (water penetration) | [mm] | 3-4 |

All data is averaged from several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.



RPM / Belgium N.V.
H. Dunantstraat 11B · B-8700 Tielt · T.:+32 (0) 51 40 38 01

Alteco Technik GmbH
Raiffeisenstraße 16 · D-27239 Twistringen · T.:+49 (0) 42 43 92 95 0

Vandex AG / Vandex International Ltd
Rötistrasse 6 · CH-4501 Solothurn · T.:+41 (0) 32 626 36 46 / 36

Vandex Isoliermittel-Gesellschaft m.b.H.
Industriestraße 21 · D-21493 Schwarzenbek · T.:+49 (0) 41 51 89 15 0